



**Molded Rubber Parts “A1”
High Precision
Tolerance Table***

Size (Inches)	Fixed	Closure	Size (Millimeters)	Fixed	Closure
Above / Including	Tolerances	Tolerances	Above / Including	Tolerances	Tolerances
0.000” - 0.100”	± .002”	± .004”	0.000 - 2.540	±0.050	±0.100
0.101” - 0.190”	± .003”	± .005”	2.570 - 4.830	±0.080	±0.130
0.191” - 0.382”	± .004”	± .006”	4.830 - 9.700	±0.100	±0.150
0.383” - 0.695”	± .005”	± .007”	9.730 - 17.650	±0.130	±0.180
0.696” - 1.064”	± .006”	± .008”	17.680 - 27.030	±0.150	±0.200
1.065” - 1.564”	± .008”	± .010”	27.050 - 39.730	±0.200	±0.250
1.565” - 2.064”	± .009”	± .011”	39.750 - 52.430	±0.230	±0.280
2.065” - 2.564”	± .010”	± .012”	52.450 - 65.130	±0.250	±0.300
2.565” - 3.064”	± .012”	± .014”	65.150 - 77.830	±0.300	±0.360
3.065” - 4.064”	± .013”	± .015”	77.850 - 103.230	±0.330	±0.380
4.065” - 5.064”	± .015”	± .017”	103.250 - 128.630	±0.380	±0.430
5.065” - 6.064”	± .016”	± .018”	128.650 - 154.030	±0.410	±0.460

Drawing designation “A1” is the tightest tolerance classification and indicates a high precision molded rubber product. Such products require complex and expensive molds, fewer cavities per mold, costly in-process controls and inspection procedures. It is desirable that the exact method of measurement be agreed upon between Robinson Rubber Products and the customer, as errors in measurement may be large in relation to the tolerance.

Some materials, particularly those requiring a post curing operation after molding, do not lend themselves to drawing designation “A1” tolerances.

*Source: RMA or Rubber Manufacturers Association