



Rubber Material Selection Guide Synthetic Natural Rubber / Synthetic Polyisoprene SNR or IR

- | | |
|--------------------------------|------------------------|
| ■ Abbreviation | SNR or IR |
| ■ ASTM D-2000 Classification | AA |
| ■ Chemical Definition | Synthetic Polyisoprene |
| ■ RRP Compound Number Category | 10000 Series |

Physical & Mechanical Properties

- | | |
|-------------------------------|-------------------|
| ■ Durometer or Hardness Range | 30 – 95 Shore A |
| ■ Tensile Strength Range | 500 – 3,500 PSI |
| ■ Elongation (Range %) | 300 % – 900 % |
| ■ Abrasion Resistance | Good to Excellent |
| ■ Adhesion to Metal | Excellent |
| ■ Adhesion to Rigid Materials | Excellent |
| ■ Compression Set | Excellent |
| ■ Flex Cracking Resistance | Excellent |
| ■ Impact Resistance | Good to Excellent |
| ■ Resilience / Rebound | Excellent |
| ■ Tear Resistance | Good to Excellent |
| ■ Vibration Dampening | Good to Excellent |

Chemical Resistance

- | | |
|---------------------------------|-------------------|
| ■ Acids, Dilute | Fair to Excellent |
| ■ Acids, Concentrated | Poor to Good |
| ■ Acids, Organic (Dilute) | Fair to Good |
| ■ Acids, Organic (Concentrated) | Good |
| ■ Acids, Inorganic | Good |
| ■ Alcohol's | Good to Excellent |



Rubber Material Selection Guide

Synthetic Natural Rubber / Synthetic Polyisoprene SNR or IR

Chemical Resistance

■ Aldehydes	Good
■ Alkalies, Dilute	Fair to Excellent
■ Alkalies, Concentrated	Fair to Good
■ Amines	Poor to Fair
■ Animal & Vegetable Oils	Poor to Good
■ Brake Fluids, Non-Petroleum Based	Good
■ Diester Oils	Poor
■ Esters, Alkyl Phosphate	Poor
■ Esters, Aryl Phosphate	Poor
■ Ethers	Poor
■ Fuel, Aliphatic Hydrocarbon	Poor
■ Fuel, Aromatic Hydrocarbon	Poor
■ Fuel, Extended (Oxygenated)	Poor
■ Halogenated Solvents	Poor
■ Hydrocarbon, Halogenated	Poor
■ Ketones	Fair to Good
■ Lacquer Solvents	Poor
■ LP Gases & Fuel Oils	Poor
■ Mineral Oils	Poor
■ Oil Resistance	Poor
■ Petroleum Aromatic	Poor
■ Petroleum Non-Aromatic	Poor
■ Refrigerant Ammonia	Good
■ Refrigerant Halofluorocarbons	R-12, R-13
■ Refrigerant Halofluorocarbons w/ Oil	Poor
■ Silicone Oil	Good
■ Solvent Resistance	Poor



Rubber Material Selection Guide Synthetic Natural Rubber / Synthetic Polyisoprene SNR or IR

Thermal Properties

- | | |
|---------------------------------------|----------------------|
| ■ Low Temperature Range | - 20° F to - 70° F |
| ■ Minimum for Continuous Use (Static) | - 60° F |
| ■ Brittle Point | - 80° F |
| ■ High Temperature Range | + 180° F to + 220° F |
| ■ Maximum for Continuous Use (Static) | + 180° F |

Environmental Performance

- | | |
|------------------------|-------------------|
| ■ Colorability | Poor |
| ■ Flame Resistance | Fair to Good |
| ■ Gas Permeability | Fair to Good |
| ■ Odor | Good to Excellent |
| ■ Ozone Resistance | Poor |
| ■ Oxidation Resistance | Good |
| ■ Radiation Resistance | Fair to Good |
| ■ Steam Resistance | Good |
| ■ Sunlight Resistance | Poor to Fair |
| ■ Taste Retention | Fair to Good |
| ■ Weather Resistance | Poor to Fair |
| ■ Water Resistance | Excellent |

For assistance in identifying the appropriate polymer or material, or to develop and formulate a polyacrylate / acrylic rubber compound to meet your specific application and performance requirements, please contact Robinson Rubber Products at e-mail: sales@robinsonrubber.com or phone: +1-763-535-6737.

Robinson Rubber Products Company, Inc. makes no expressed or implied warranty as to any qualities, attributes, or characteristics of any polymer or material. This information is provided for reference only.